

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 : D01F 6/80, 6/60, 6/68, 1/10	A1	(11) International Publication Number: WO 94/18364 (43) International Publication Date: 18 August 1994 (18.08.94)
(21) International Application Number: PCT/US93/01278 (22) International Filing Date: 12 February 1993 (12.02.93) (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventor: KIDDER, David, Roy; 900 Heritage Drive, Seaford, DE 19973 (US). (74) Agents: HENDRICKSON, John, S. et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: PROCESS FOR MAKING POLYAMIDE FIBER USEFUL AS STAPLE FOR PAPERMAKING MACHINE FELT

(57) Abstract

The invention provides a process for making polyamide fiber with high molecular weight and/or chemical and thermal resistance using conventional single or twin screw extruders. The process includes: melt-blending polyamide polymer comprising at least about 75 % by weight of poly(hexamethylene adipamide) or poly(ϵ -caproamide) and having a formic acid relative viscosity of about 20 to about 50 with a polyamide additive concentrate comprising polyamide polymer and an additive selected from the class consisting of stabilizers, catalysts and mixtures thereof to form a molten polymer which contains about 0.05 to about 2 weight % of the additive; and extruding the molten polymer from a spinneret and forming a fiber having a denier per filament of 1 to 40. Fibers made by this process have great utility in the batt of papermaking machine felts where they provide improved resistance to wear and/or chemical attack.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GK	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE

Process for Making Polyamide Fiber
Useful as Staple for Papermaking Machine Felt

BACKGROUND OF THE INVENTION

5 This invention relates to processes for making polyamide fiber and more particularly to a process for making polyamide fiber which contains additives including catalysts, stabilizers or both and the products made thereby which are particularly useful as staple for papermaking machine felt.

10 Stabilizers are often added to polyamides such as nylon 66, poly(hexamethylene adipamide), and nylon 6, poly(ϵ -caproamide), for the purpose of reducing thermal degradation and chemical attack. High levels of such stabilizers are desirable when the intended use of such fiber is in an environment with particularly harsh conditions. One such use of polyamide fiber is as staple used as in papermaking machine felts. Such felts are often exposed to
15 highly alkaline, oxidizing aqueous solutions which can seriously shorten the service life of the felt.

There are several known methods for adding the stabilizing agents to polyamides. One method is to introduce a solution of the stabilizer into an autoclave during the polymerization step. The amount of stabilizer which can be
20 introduced by this method is limited, however, due to the violent foaming that occurs during autoclave polymerization when stabilizers are added in solution form. A similar reaction occurs when large amounts of stabilizer solutions are added to continuous polymerizers. The normal maximum concentration in polyamides on commercial autoclaves and continuous polymerizers using this
25 method is typically 0.05 weight %.

For fiber to be used for papermaking machine felts, it is also desirable sometimes to spin polyamides which have a high formic acid relative viscosity to improve resistance to wear from flexing, impact and abrasion. It has been demonstrated that an increase in molecular weight of a polyamide will
30 increase the toughness, modulus of elasticity, and impact resistance. However, when the polyamide supply for such fiber is polyamide flake, it is often difficult to obtain the desired high relative viscosity while maintaining polymer quality, i.e., low level of cross-branching. While it would be desirable to increase the relative viscosity in the flake by using a high quantity of catalyst in an autoclave, it has
35 been found that difficulties similar to those encountered with stabilizers can occur when attempting to add catalysts in high quantity. In addition, high quantities of catalyst in the autoclave can cause severe injection port pluggage and complications to injection timings during autoclave cycles. High quantities of

catalysts injected into continuous polymerizers place stringent demands on equipment capability because of high levels of waterloading.

SUMMARY OF INVENTION

The invention provides a process for making polyamide fiber
5 including:

melt-blending polyamide polymer comprising at least about 75% by weight of poly(hexamethylene adipamide) or poly(ϵ -caproamide) and having a formic acid relative viscosity of about 20 to about 50 with a polyamide additive concentrate comprising polyamide polymer and an additive selected from the
10 class consisting of stabilizers, catalysts and mixtures thereof to form a molten polymer which contains about 0.05 to about 2 weight % of the additive; and extruding the molten polymer from a spinneret to form a fiber having a denier per filament of 1 to 40.

In one preferred form of the invention, the additive is a catalyst
15 selected from the class consisting of alkali-metal, alkyl-substituted and/or aryl-substituted phosphites; alkali-metal, alkyl-substituted and/or aryl-substituted phosphates; alkyl-substituted and/or aryl-substituted phosphonic acids; alkyl-substituted and/or aryl-substituted phosphinic acids; and mixtures thereof and the relative viscosity of the polyamide polymer is increased prior to extruding. Most
20 preferably, the relative viscosity of the polymer is increased by at least about 30 units and is increased such that the residence time of the additive in the molten polymer before extruding is not more than about 60 minutes.

In another preferred form of the invention, the additive is a stabilizer selected from the class consisting of alkyl-substituted and/or aryl-
25 substituted phenols; alkyl-substituted and/or aryl-substituted phosphites; alkyl-substituted and/or aryl-substituted phosphonates; and mixtures thereof.

The invention is capable of adding high amounts of stabilizers and/or catalysts to polyamides which could not be done effectively otherwise and is particularly desirable for polyamides being processed on single or twin screw-
30 melter extruders. The invention is capable of increasing the relative viscosity of a polyamide while maintaining excellent polymer quality.

DETAILED DESCRIPTION

Polyamides used for the main polymer source in the process in accordance with the invention and which constitute the resulting fibers are at
35 least about 75 weight % poly(hexamethylene adipamide) (nylon 66) or at least about 75 weight % poly(ϵ -caproamide) (nylon 6). Generally, for industrial use where strength and thermal stability are important, it is preferable for the amount of comonomers and other polyamides mixed with the poly(hexamethylene

adipamide) or poly(ϵ -caproamide) to be less than about 5 weight %. Because of a balance of properties including dimensional stability which is imparted to the resulting fiber and reasonable melt-processing temperatures, homopolymer poly(hexamethylene adipamide) (6,6 nylon) is the most preferred polyamide for the main polymer source in the practice of the present invention. The formic acid relative viscosity of the main polyamide used is about 20 to about 50.

The additive concentrates useful in accordance with the present invention can contain one or more of a wide variety of generally linear, aliphatic polycarbonamide homopolymers and copolymers. For example, homopolymer poly(hexamethylene adipamide) (nylon 66), poly(ϵ -caproamide) (nylon 6), and poly(tetramethylene adipamide) (nylon 46) can be used. Other polyamides which may be used are poly(aminoundecanoamide), poly(aminododecanoamide), polyhexamethylene sebacamide, poly(p-xylylene-azelaamide), poly(m-xylylene adipamide), polyamide from bis(p-aminocyclohexyl)methane and azelaic, sebacic and homologous aliphatic dicarboxylic acids. Copolymers and mixtures of polyamides also can be used. It is preferable for the polyamide used in the concentrate to have a melting point not more than the melting point of the main polyamide and a similar melt viscosity to the main polyamide to facilitate the melt-blending step of the process which will be explained in more detail hereinafter.

When the fiber is for use as felt in a papermaking machine, it is preferable for both the main polyamide and the concentrate to be free of the copper (often added as CuI to polyamides for the purpose of ultraviolet radiation protection) since the presence of copper in the felt fiber catalyzes chemical degradation of the fiber when exposed to chemical compounds such as hypochlorite bleach used in the papermaking process.

The additive in the concentrate is a stabilizer, catalyst or mixture of a stabilizer and a catalyst. Preferred stabilizers are alkyl-substituted and/or aryl-substituted phenols; alkyl-substituted and/or aryl-substituted phosphites; alkyl-substituted and/or aryl-substituted phosphonates; and mixtures thereof. Preferred catalysts are alkali-metal, alkyl-substituted, and/or aryl-substituted phosphites; alkali-metal, alkyl-substituted, and/or aryl-substituted phosphates; alkyl-substituted and/or aryl-substituted phosphonic acids; alkyl-substituted and/or aryl-substituted phosphinic acids; and mixtures thereof.

Most preferably, the additive is 1,3,5-trimethyl-2,4,6-tris (3,5-tertbutyl-4-hydroxybenzyl) benzene (sold by Ciba-Geigy under the trademark IRGANOX 1330), N,N'-hexamethylene bis (3,5-di-tert-butyl-4-hydroxyhydrocinnamamide) (sold by Ciba-Geigy under the trademark IRGANOX 1098, and

tris (2,4-di-tert-butylphenyl) phosphite (sold by Ciba-Geigy under the trademark IRGAFOS 168 in combination with IRGANOX antioxidants, e.g., IRGANOX B 1171 is a mixture of IRGAFOS 168 and IRGANOX 1098 in equal quantities by weight.) It should be noted that alkali-metal, alkyl-substituted, and/or aryl-substituted phosphites such as the compound tris (2,4-di-tert-butylphenyl) phosphite (IRGAFOS 168) can operate as both a stabilizer and a catalyst and, if desired, a mixture of compounds can be used to provide both stabilizer and catalyst functions.

The additive concentrates are made from polyamide polymer and the additives using an intermixer such as a Hogarth blender or the components are melt-blended in a twin screw extruder or like device. The molten mixture is then cast as flake or pellets. Preferably, the amount of additive in the concentrate is about 1 to about 40 weight %.

The concentrate is melt-blended with polyamide from the main polymer source to form a molten polymer which contains about 0.05 to about 2 weight % of the additive, preferably, about 0.1 to about 0.7 weight %. This is preferably accomplished by mixing the polymer from the main source with the concentrate with both in solid particulate form to provide a particulate blend prior to melt-blending. The appropriate proportions of the main polyamide and the concentrate are provided by metering using a gravimetric or volumetric feeder for the concentrate which meters the concentrate through an opening into the main polymer flake supply chute supplying the feed zone of the extruder. A single or twin screw-melter/extruder is suitable for melt-blending. The resulting molten polymer is preferably directly supplied to the polymer transfer line piping for conveyance to the spinneret and, if desired, can be blended further in the transfer line there using inline static mixers such as those sold under the trademark KENICS or under the trademark KOCH, flow inverters or both.

Other methods for melt-blending can be used such as mixing molten polymer from the main source with a molten concentrate or any other appropriate method which provides a homogenous molten polymer mixture containing the additive.

After extrusion into the transferline, the polyamide mixture is supplied by metering pump to a spinneret and extruded and formed into fiber. This can be accomplished using techniques which are well known in the art. For use as staple for papermaking machine felt, the polymer is extruded then drawn as a multifilament yarn or tow and cut to form staple as is also known in the art. The resulting staple fiber can be used in the known manner, e.g., incorporated into a felt for a papermaking machine.

When the additive is a catalyst for the purpose of increasing the formic acid relative viscosity (RV), it is preferable for the relative viscosity to be increased by at least about 30 RV units. In addition, to minimize the opportunity for polymer degradation, the melt blending should be performed in close proximity to said spinneret, e.g., just prior to the transfer line which supplies the polymer to the metering pumps for the spinnerets. Preferably, the average residence time of the catalyst in said molten polymer before extruding is not more than about 60 minutes. For the increase in relative viscosity to occur efficiently in the transfer line in the preferred embodiment of the invention, the polyamide has a low water content, preferably less than 0.03 weight % when the average hold up time in the transfer line is 5 to 7 minutes. It is possible to increase the relative viscosity to extremely high levels, e.g., from 60 RV to 216 RV with a under such conditions.

The relative viscosity increase can be controlled to a desired level by modifying the proportions of the supply polymer and concentrate, moisture level and concentration of catalyst in the concentrate. Moisture level can be controlled by flake conditioning before melt-blending and by venting during melt-blending. Because this form of the invention increases relative viscosity only in the transfer line, there is no need for specially modified separator/finisher equipment, etc. on continuous polymerizers or solid phase polymerization or additional flake conditioning capacity on flake-fed melt extruder systems.

Polyamide fiber in accordance with the invention is useful as staple for papermaking machine felt. The fiber denier per filament is 1 to 40 and comprises at least 75 weight % poly(hexamethylene adipamide) polymer. The polymer contains about 0.1 to about 2.0 weight % of a stabilizer selected from the class consisting of 1,3,5-trimethyl-2,4,6-tris (3,5-tertbutyl-4-hydroxybenzyl) benzene, N,N'-hexamethylene bis (3,5-di-tert-butyl-4-hydroxyhydro-cinnamamide), and tris (2,4-di-tert-butylphenyl) phosphite and mixtures thereof, the fiber being substantially free of copper. Preferably, the fiber contains about 0.1 to about 0.7 weight % of the stabilizer. In the fiber, the stabilizer is preferably thoroughly mixed with the polyamide in the fiber.

Preferably, the formic acid relative viscosity of the polyamide of the fiber is at least about 20, most preferably, at least about 35. The most preferred polyamide is at least about 95% poly(hexamethylene adipamide).

Fiber in accordance with the invention used as staple in the batt of papermaking machine felts provides increased service life when compared to conventional staple fiber.

TEST METHODS

Relative viscosity of polyamides refers to the ratio of solution and solvent viscosities measured in capillary viscometer at 25°C. The solvent is formic acid containing 10% by weight of water. The solution is 8.4% by weight polyamide polymer dissolved in the solvent.

Denier: Denier or linear density is the weight in grams of 9000 meters of yarn. Denier is measured by forwarding a known length of yarn, usually 45 meters, from a multifilament yarn package to a denier reel and weighing on a balance to an accuracy of 0.001 g. The denier is then calculated from the measured weight of the 45 meter length.

Tensile Properties: Tenacity and Elongation to break are measured as described by Li in U.S. Patent No. 4,521,484 at col. 2, line 61 to col. 3, line 6. % Work to Break is the area under the stress-strain curve.

EXAMPLES

In the examples which follow, the additives are identified by their trademarks as indicated below:

1,3,5-trimethyl-2,4,6-tris (3,5-tertbutyl-4-hydroxybenzyl) benzene - IRGANOX 1330

N,N'-hexamethylene bis (3,5-di-tert-butyl-4-hydroxyhydro-cinnamamide) - IRGANOX 1098

Tris (2,4-di-tert-butylphenyl) phosphite in equal quantities with IRGANOX 1098 - IRGANOX B 1171

EXAMPLE 1

The staple fibers shown in Table 1 were made by volumetrically metering concentrate pellets of 20% IRGANOX B 1171 co-melted with 80% mixed polyamide carrier (sold by Du Pont under the trademark ELVAMIDE) into the main polyamide flake (homopolymer nylon 66) feed at a rate such that the particulate mixture contains 0.4 weight % IRGANOX B 1171. The concentrate pellets and main polyamide were then melted-blended at 290°C in a vented, twin screw extruder. The polymer was extruded into a transfer line with a 5 to 7 minute holdup time to a manifold feeding meter pumps at 80 pounds per hour per position. The polymer relative viscosity was 68-72 controlled by varying the vacuum on the barrel of the twin screw. The fiber was extruded through spinnerets in filament form, air quenched, coated with finish (1.0% to 1.5%) and partially drawn to 60 dpf. The spun fibers were then collected in tow form, drawn and crimped to 15 dpf using a 4.0 draw ratio on a draw crimper. The drawn/crimped fibers were crimp set in a steam autoclave at 135°C, dried, then cut as 3 inch staple using a lumus cutter. The fibers had a tenacity of 4.0 to 6.0

WO 94/18364

gpd and an elongation to break of 80%-100%. The same technique was used to make the different concentrations of IRGANOX 1330 and IRGANOX 1098 in nylon 66 shown in Table 1 except the stabilizer concentrate pellets were made by combining 20% stabilizer with homopolymer nylon 6 instead of the mixed polyamide carrier sold under the trademark ELVAMIDE.

- 5 Test fibers made as described above were exposed to 1000 ppm . NaOCl @ 80°C, 72hrs; 3% H₂O₂ @ 80°C, 72hrs; and dry heat @ 130°C for 72hrs. Denier, tenacity and elongation of each test fiber was checked before and after exposure to the chemical and dry heat tests. The % work to break (area under stress strain curve) change was determined and is an index of the increased protection provided by the addition of stabilizers in accordance with the invention compared with a control with no stabilizer. A summary of results is shown in Table 1.

TABLE 1

20	Sample Description	Chemical Stability % Retained Work-To-Break NaOCl H ₂ O ₂		Dry Heat Stability % Retained Work-To-Break 130°C 72 Hours
25	Control	9	23	20
30	Nylon 66 + 0.4 weight% IRGANOX B1171	27	61	91
35	Nylon 66 + 0.05 weight% IRGANOX 1330	13	30	64
40	Nylon 66 + 0.2 weight% IRGANOX 1330	9	22	54
	Nylon 66 + 0.3 weight% IRGANOX 1098	7	71	100

EXAMPLE 2

This example illustrates the significant increase in relative viscosity that is possible when a catalyst is used in a process in accordance with the invention. A 10 weight % concentrate of IRGANOX B 1171 in a mixed polyamide carrier (sold by Du Pont under the trademark ELVAMIDE) is melt-blended with homopolymer nylon 66 that has a weight % water of less than 0.03% in a twin screw extruder. The amount of water the nylon 66 is reduced prior to melt-blending by flake conditioning. As shown in Table 2, the relative viscosity is increased by the volumetric feeding of IRGANOX B 1171 concentrate pellets into the main nylon 66 flake feed when the weight % water in the polyamide flake is at the reduced level of less than about 0.03 weight %. Staple fiber was made as in Example 1. There was no increase in the level of machine breaks or broken filaments of the high relative viscosity test item compared to the control.

TABLE 2

Sample Description	RV	RV Increase
Control Nylon 66, <0.3% Water With No IRGANOX B 1171	60	--
Test Item Nylon 66, <0.3 Water + 0.1 weight% IRGANOX B 1171	70-75	9-15

CLAIMS:

1. A process for making polyamide fiber comprising:
melt-blending polyamide polymer comprising at least about 75% by
weight of poly(hexamethylene adipamide) or poly(ϵ -caproamide) and having a
5 formic acid relative viscosity of 20-50 with a polyamide additive concentrate
comprising polyamide polymer and an additive selected from the class consisting
of stabilizers, catalysts and mixtures thereof to form a molten polymer which
contains about 0.05 to about 2 weight % of said additive; and
extruding said molten polymer from a spinneret and forming a fiber
10 having a denier per filament of 1 to 40.
2. The process of claim 1 wherein said additive is a catalyst
selected from the class consisting of alkali-metal, alkyl-substituted, and/or aryl-
substituted phosphites; alkali-metal, alkyl-substituted, and/or aryl-substituted
15 phosphates; alkyl-substituted and/or aryl-substituted phosphonic acids; alkyl-
substituted and/or aryl-substituted phosphinic acids; and mixtures thereof and
said relative viscosity of said polyamide polymer is increased prior to extruding
from said spinneret.
3. The process of claim 2 wherein said relative viscosity of said
polymer is increased by at least about 30 units.
- 20 4. The process of claim 2 wherein said melt-blending is performed
in such that the average residence time of said catalyst in said molten polymer
before extruding is not more than about 60 minutes.
5. The process of claims 1 wherein said additive is a stabilizer
selected from the class consisting of alkyl-substituted and/or aryl-substituted
25 phenols; alkyl-substituted and/or aryl-substituted phosphites; alkyl-substituted
and/or aryl-substituted phosphonates; and mixtures thereof.
6. The process of claim 1 wherein said additive is selected from the
class consisting of 1,3,5-trimethyl-2,4,6-tris (3,5-tertbutyl-4-hydroxybenzyl)
benzene, N,N'-hexamethylene bis (3,5-di-tert-butyl-4-hydroxyhydro-
30 cinnamamide), and tris (2,4-di-tert-butylphenyl) phosphite and mixtures thereof.
7. The process of claim 1 wherein said fiber is free of copper.
8. The process of claim 1 wherein said concentrate contains about
1 to about 40 weight % of additive in polyamide polymer.
9. The process of claim 1 wherein said resulting molten polymer
35 contains about 0.1 to about 0.7 weight % of said additive.
10. The process of claim 1 wherein said polyamide polymer and
said polyamide stabilizer concentrate are in solid particulate form and are mixed
together to form a particulate blend prior to melt-blending.

11. The process of claim 10 wherein said melt-blending is performed using a screw-melter.

12. The process of claims 1 wherein said polyamide polymer is homopolymer poly(hexamethylene adipamide).

5 13. Polyamide fiber useful as staple for paper making machine felt comprising 1 to 40 denier per filament fiber of at least 75 weight % poly(hexamethylene adipamide) polymer and containing about 0.1 to about 2.0 weight % of a stabilizer selected from the class consisting of 1,3,5-trimethyl-2,4,6-
10 tris (3,5-tertbutyl-4-hydroxybenzyl) benzene, N,N'-hexamethylene bis (3,5-di-tert-butyl-4-hydroxyhydro-cinnamamide), and tris (2,4-di-tert-butylphenyl) phosphite and mixtures thereof, said fiber being substantially free of copper.

14. The fiber of claim 13 comprising about 0.1 to about 0.7 weight % of said stabilizer.

15 15. The fiber of claim 13 wherein the formic acid relative viscosity of said polyamide is at least about 20.

16. The fiber of claim 13 wherein said polyamide polymer is at least about 95% poly(hexamethylene adipamide).

INTERNATIONAL SEARCH REPORT

PCT/US 93/01278

International Application No.		
I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ^a According to International Patent Classification (IPC) or to both National Classification and IPC IPC ⁵ : D 01 F 6/80, D 01 F 6/60, D 01 F 6/68, D 01 F 1/10		
II. FIELDS SEARCHED		
Minimum Documentation Searched ^b		
Classification System	Classification Symbols	
IPC ⁵	D 01 F	
Documentation Searched other than Minimum Documentation to the extent that such Documents are included in the Fields Searched ^c		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ^d		
Category ^e	Citation of Document, " with indication, where appropriate, of the relevant passages ¹²	
	Relevant to Claim No. ¹³	
A	US, A, 3 493 633 (LANGE) 03 February 1970 (03.02.70), claims; example 1. --	1, 5-9, 12-14, 16
A	US, A, 3 558 569 (GOTO et al.) 26 January 1971 (26.01.71), claims. --	1, 2, 5, 8, 9
A	DERWENT ACCESSION, no. 74-046 51V, Questel Telesystems (WPIL), DERWENT PUBLICATION LTD., London, abstract & JP, A, 48-015 957 (TEJIN LTD.) 28 February 1973 (28.02.73). --	1, 2, 7
A	DERWENT ACCESSION, no. 73-399 84U,	1, 2, 7, 8, 9, 12
<p>^a Special categories of cited documents: ¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search	Date of Mailing of this International Search Report	
07 October 1993	-2.11.93	
International Searching Authority	Signature of Authorized Officer	
EUROPEAN PATENT OFFICE	WEIGERSTORFER e.h.	

Form PCT/ISA/210 (second sheet) (January 1985)

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, " with indication, where appropriate, of the relevant passages	Relevant to Claim No.
	Questel Telesystems (WPIL), DERWENT PUBLICATIONS LTD., London, abstract & JP,B,73-023 103 (ASAHI CHEMICAL IND. CO. LTD.) 1973. -----	

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

In diesem Anhang sind die Mitglieder
der Patentfamilien der im obenge-
nannten internationalen Recherchenbericht
angeführten Patentedokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

ANNEX

to the International Search
Report to the International Patent
Application No.

PCT/US 93/01278 SAE 71091

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visé ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

Im Recherchenbericht angeführtes Patentedokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A 3493633	03-02-70	keine - none - rien	
US A 3558569	26-01-71	keine - none - rien	

